## HYTAC® - C

Castable syntactic tooling

HYTAC-C is a one-part castable product in the HYTAC family of syntactics. This product is available as an uncured, single component mixture that may be poured or cast into a wide variety of shapes and sizes. Provided in 1-gallon containers, the pre-mixed syntactic flows smoothly into any tool or cavity.

## After curing, HYTAC-C exhibits the same properties found in CMT's HYTAC-W:

- Low thermal conductivity and specific heat
- Dimensionally stable
- Excellent temperature resistance to 355°F
- Lightweight
- Easily machined

## **Typical Properties**

Color	White
Density (ρ)	44 lb/ft <sup>3</sup> [705 kg/m <sup>3</sup> ]
Thermal Conductivity (k)	0.16 BTU/hr-ft-°F [0.18 W/m°K]
Coefficient of Thermal Expansion(CTE)	17 x 10 <sup>-6</sup> in/in° F [67.7 x 10 <sup>-6</sup> m/m/°C]
Compressive Strength	8,000 psi [55 Mpa]
Service Temperature	350°F [176 °C]



## **Applications**

HYTAC-C is shipped as a single component, liquid syntactic material that may be poured or cast at a customer site into any tool or cavity. While this material is temperature-sensitive and requires special handling, it is often a viable alternative to extensive machining of plug shapes. Contact CMT to discuss your application needs.



CMT Materials, Inc. 107 Frank Mossberg Drive Attleboro, MA 02703 USA T: +1-508-226-3901 F: +1-508-226-3902 Email: info@cmtmaterials.com

Available in 1-gallon pails

www.cmtmaterials.com